

KLINGELE

PAPIERWERKE

Technische Spezifikation technical specification

Testliner 3

Eigenschaft property											
Flächengewicht [g/m ²] <i>grammage [gsm]</i> DIN EN ISO 536	Ø	100 ± 3%	110 ± 3%	120 ± 3%	125 ± 3%	130 ± 3%	135 ± 3%	140 ± 3%	150 ± 3%	160 ± 3%	170 ± 3%
Feuchte [%] <i>moisture content</i>	Ø	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0	8,0 ± 1,0
Streifenstauchwiderstand, SCT _{quer} [kN/m] <i>compressive strength CD</i> DIN 54518	min.	1,90	2,00	2,10	2,20	2,30	2,35	2,40	2,55	2,70	2,80
Berstdruck [kPa] <i>bursting strength</i> DIN EN ISO 2758	min.	240	250	260	270	280	290	300	320	340	350
Luftdurchlässigkeit, Bendtsen [ml/min.] <i>porosity</i> DIN 53120/1	Ø	240-280	220-280	200-270	190-250	190-250	190-250	180-240	180-220	180-220	160-220
Cobb60-Test, Oberseite [g/m ²] (<i>optional</i>) <i>cobb60-test [gsm] (optional)</i> DIN EN 20535	max.	30-60	30-60	30-60	30-60	30-60	30-60	30-60	30-60	30-60	30-60

Testbedingungen / test conditions: 23°C, 50% RH

01.06.2011

Verkauf Weener/ sales department Weener

Fax: +49 4951 303 52

Micha Meyer (sales manager)

micha.meyer@klingele.com

+49 163 77 22 345 (mobile)

+49 4951 303 24

Martina Bakker (disposition + logistics)

martina.bakker@klingele.com

+49 4951 303 23