

KLINGELE

P A P I E R W E R K E

Technische Spezifikation technical specification

Wellenstoff fluting, corrugated medium

Eigenschaft property												
Flächengewicht [g/m ²] grammage [gsm] DIN EN ISO 536	Ø	100 ± 3%	105 ± 3%	110 ± 3%	115 ± 3%	120 ± 3%	125 ± 3%	130 ± 3%	135 ± 3%	140 ± 3%	150 ± 3%	160 ± 3%
Feuchte [%] moisture content	Ø	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0	7,5 ± 1,0
Streifenstauchwiderstand, SCT _{quer} [kN/m] compressive strength CD DIN 54518	min.	1,90	1,95	2,00	2,05	2,10	2,20	2,25	2,30	2,40	2,50	2,60
Flachstauchwiderstand, CMT ₃₀ [N] concora medium test DIN EN ISO 7263	min.	165	175	180	185	190	200	205	210	220	230	240
Luftdurchlässigkeit, Bendtsen [ml/min.] porosity DIN 53120/1	Ø	240-280	240-280	220-280	220-270	200-270	190-250	190-250	190-250	180-240	180-230	160-220

Testbedingungen / test conditions: 23°C, 50% RH

01.06.2011

Verkauf Weener/ sales department Weener

Fax: +49 4951 303 52

Micha Meyer (sales manager)

micha.meyer@klingele.com

+49 163 77 22 345 (mobile)

+49 4951 303 24

Martina Bakker (disposition + logistics)

martina.bakker@klingele.com

+49 4951 303 23