

Technical Specifications

GRADE DESCRIPTION	Nominal grammage [g/m ²]	Moisture content [%]	SCT cd		Bursting strength		CMT 30	
			[kN/m]	[kPa]	[N]	[N]		
Test Method	ISO 536	ISO 287	DIN 54518		ISO 2759		ISO 7263	
Tolerance	+/- 3%		typ.	min.	typ.	min.	typ.	min.
Flexliner 120	120		2,20	2,10	300	290	190	180
Flexliner 125	125		2,25	2,15	310	300	195	185
Flexliner 130	130		2,30	2,20	320	310	200	190
Flexliner 135	135	7 – 9	2,35	2,25	330	320	210	200
Flexliner 140	140		2,50	2,40	335	325	220	210
Flexliner 150	150		2,60	2,50	350	340	230	220
Flexliner 160	160		2,70	2,60	370	360	235	225

Test conditions 23°C | 50% RH | ISO 187

Weener sales department

Micha Meyer | sales manager
 micha.meyer@klinge.de
 +49 163 77 22 345
 +49 4951 303 24

Technical customer service

Michael Michels | technical customer service
 michael.michels@klinge.de
 +49 173 95 80 442
 +49 4951 303 45

