

Brown testliner | CEPI Code 20

Technical Specifications

GRADE DESCRIPTION	Nominal grammage [g/m ²]	Moisture content [%]	Cobb 60 sec [g/m ²]	Cobb 1800 sec [g/m ²]	SCT cd [kN/m]		Bursting strength [kPa]	
Test Method	ISO 536	ISO 287	DIN 535	DIN 535	DIN 54518		ISO 2759	
Tolerance	+/- 3%	+/- 1%			typ.	min.	typ.	min.
Testliner 150	150				2,60	2,50	350	340
Testliner 160	160				2,70	2,60	370	360
Testliner 170	170	9	max. 30	max. 70	2,80	2,70	380	370
Testliner 180	180				2,90	2,80	390	380

Test conditions 23°C | 50% RH | ISO 187

Weener sales department

Micha Meyer | sales manager
 micha.meyer@klinge.de
 +49 163 77 22 345
 +49 4951 303 24

Technical customer service

Michael Michels | technical customer service
 michael.michels@klinge.de
 +49 173 95 80 442
 +49 4951 303 45

