

Fluting

effective from 01/2018

Recycled fibre based medium | CEPI Code 41

Technical Specifications

GRADE DESCRIPTION	Nominal grammage	Moisture content	SCT cd		CMT 30	
	[g/m ²]	[%]	[kN/m]		[N]	
Test Method	ISO 536	ISO 287	DIN 54518		ISO 7263	
Tolerance	+/- 3%		typ.	min.	typ.	min.
Fluting 115	115	7 - 9	2,10	2,00	180	170
Fluting 120	120		2,20	2,10	190	180
Fluting 125	125		2,25	2,15	195	185
Fluting 130	130		2,30	2,20	200	190
Fluting 135	135		2,35	2,25	210	200
Fluting 140	140		2,50	2,40	220	210
Fluting 150	150		2,60	2,50	230	220
Fluting 160	160		2,70	2,60	235	225

Test conditions 23°C | 50% RH | ISO 187

Weener sales department

Micha Meyer | sales manager
 micha.meyer@klingele.com
 +49 163 77 22 345
 +49 4951 303 24

Technical customer service

Michael Michels | technical customer service
 michael.michels@klingele.com
 +49 173 95 80 442
 +49 4951 303 45



KLINGELE
 PAPER & PACKAGING GROUP

Klingele Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klingele-Str. 1 · 26826 Weener
 Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klingele.com · www.klingele.com