

# Testliner 2

effective from 01/2018

Brown testliner 2 | CEPI Code 20

## Technical Specifications

GRADE DESCRIPTION	Nominal grammage	Moisture content	SCT cd		Bursting strength	
	[g/m <sup>2</sup> ]	[%]	[kN/m]		[kPa]	
Test Method	ISO 536	ISO 287	DIN 54518		ISO 2759	
Tolerance	+/- 3%		typ.	min.	typ.	min.
Testliner 125	125	7 – 9	2,35	2,25	340	330
Testliner 140	140		2,50	2,40	360	350
Testliner 160	160		2,80	2,70	400	390
Cobb 60 sec DIN 535			max. 40			

Test conditions 23°C | 50% RH | ISO 187

### Weener sales department

Micha Meyer | sales manager  
micha.meyer@klingele.com  
+49 163 77 22 345  
+49 4951 303 24

### Technical customer service

Michael Michels | technical customer service  
michael.michels@klingele.com  
+49 173 95 80 442  
+49 4951 303 45



**KLINGELE**  
PAPER & PACKAGING GROUP

Klingele Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klingele-Str. 1 · 26826 Weener  
Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klingele.com · www.klingele.com