

Testliner 2 dark

effective from 01/2018

Brown testliner 2 | CEPI Code 20

Technical Specifications

GRADE DESCRIPTION	Nominal grammage	Moisture content	SCT cd		Bursting strength	
	[g/m ²]	[%]	[kN/m]		[kPa]	
Test Method	ISO 536	ISO 287	DIN 54518		ISO 2759	
Tolerance	+/- 3%		typ.	min.	typ.	min.
Testliner 125	125	7 – 9	2,35	2,25	340	330
Testliner 130	130		2,40	2,30	345	335
Testliner 140	140		2,50	2,40	360	350
Testliner 160	160		2,80	2,70	400	390
Testliner 170	170		2,90	2,80	410	400
Cobb 60 sec DIN 535	max. 40					

Test conditions 23°C | 50% RH | ISO 187

Weener sales department

Micha Meyer | sales manager
micha.meyer@klingele.com
+49 163 77 22 345
+49 4951 303 24

Technical customer service

Michael Michels | technical customer service
michael.michels@klingele.com
+49 173 95 80 442
+49 4951 303 45



KLINGELE
PAPER & PACKAGING GROUP

Klingele Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klingele-Str. 1 · 26826 Weener
Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klingele.com · www.klingele.com