

Fluting

effective from 01/2021

Recycled fibre based medium | CEPI Code 41

Technical Specifications

GRADE DESCRIPTION	Nominal grammage [g/m ²]	Moisture content [%]	SCT cd		CMT 30	
			[kN/m]		[N]	
Test Method	ISO 536	ISO 287	DIN 54518		ISO 7263	
Tolerance	+/- 3%		typ.	min.	typ.	min.
Fluting 120	120		2,20	2,10	190	180
Fluting 125	125		2,25	2,15	195	185
Fluting 130	130		2,30	2,20	200	190
Fluting 135	135	7 – 9	2,35	2,25	210	200
Fluting 140	140		2,50	2,40	220	210
Fluting 150	150		2,60	2,50	230	220
Fluting 160	160		2,70	2,60	235	225

Test conditions 23°C | 50% RH | ISO 187

Weener sales department

Micha Meyer | sales manager
micha.meyer@klinge.de
+49 163 77 22 345
+49 4951 303 24

Technical customer service

Michael Michels | technical customer service
michael.michels@klinge.de
+49 173 95 80 442
+49 4951 303 45



KLINGELE
P A P I E R W E R K E

Klinge Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klinge-Str. 1 · 26826 Weener
Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klinge.de · www.klinge.de