

# Testliner 2

effective from 01/2021

Brown testliner 2 | CEPI Code 20

## Technical Specifications

GRADE DESCRIPTION	Nominal grammage [g/m <sup>2</sup> ]	Moisture content [%]	SCT cd		Bursting strength		
			[kN/m]		[kPa]		
Test Method	ISO 536	ISO 287	DIN 54518		ISO 2759		
Tolerance	+/- 3%		typ.	min.	typ.	min.	
Testliner 120	120	7 - 9	2,25	2,15	330	320	
Testliner 125	125		2,35	2,25	340	330	
Testliner 130	130		2,40	2,30	350	340	
Testliner 140	140		2,50	2,40	360	350	
Testliner 160	160		2,80	2,70	400	390	
Testliner 170	170		2,95	2,85	420	410	
Testliner 180	180		3,10	3,00	440	430	
Cobb 60 sec DIN 535			max. 40 g/m <sup>2</sup>				

Test conditions 23°C | 50% RH | ISO 187

### Weener sales department

Micha Meyer | sales manager  
micha.meyer@klingele.com  
+49 163 77 22 345  
+49 4951 303 24

### Technical customer service

Michael Michels | technical customer service  
michael.michels@klingele.com  
+49 173 95 80 442  
+49 4951 303 45



**KLINGELE**  
P A P I E R W E R K E

Klingele Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klingele-Str. 1 · 26826 Weener  
Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klingele.com · www.klingele.com