

Testliner 3

Gültig ab 01/11/2014

Brown testliner 3 | CEPI Code 30

Technical Specifications

GRADE DESCRIPTION	Nominal grammage	Moisture content	SCT cd		Bursting strength		
	[g/m ²]	[%]	[kN/m]		[kPa]		
Test Method	ISO 536	ISO 287	DIN 54518		ISO 2759		
Tolerance	+/- 3%	+/- 1%	Ø	min.	Ø	min.	
Testliner 120	120	8,0	2,00	1,90	260	250	
Testliner 125	125		2,05	1,95	270	260	
Testliner 130	130		2,15	2,05	280	270	
Testliner 135	135		2,20	2,10	290	280	
Testliner 140	140		2,25	2,15	305	295	
Testliner 150	150		2,35	2,25	315	305	
Testliner 160	160		2,50	2,40	335	325	
Testliner 170	170		2,65	2,55	350	340	
OPTIONAL							
Cobb 60 sec DIN 535	Testliner 120-170		max. 30-60				
Cobb 1800 sec DIN 535	Testliner 120-170		max. 70-90				

Test conditions 23°C | 50% RH | ISO 187

Weener Sales department

Micha Meyer | sales manager
micha.meyer@klinge.de
+49 163 77 22 345
+49 4951 303 24

Technical customer service

Michael Michels | technical customer service
michael.michels@klinge.de
+49 173 95 80 442
+49 4951 303 92 359



KLINGELE
P A P I E R W E R K E