

# Fluting

effective from 01/2018

Recycled fibre based medium | CEPI Code 41

## Technical Specifications

GRADE DESCRIPTION	Nominal grammage	Moisture content	SCT cd		CMT 30	
	[g/m <sup>2</sup> ]	[%]	[kN/m]		[N]	
Test Method	ISO 536	ISO 287	DIN 54518		ISO 7263	
Tolerance	+/- 3%		typ.	min.	typ.	min.
Fluting 115	115	7 - 9	2,10	2,00	180	170
Fluting 120	120		2,20	2,10	190	180
Fluting 125	125		2,25	2,15	195	185
Fluting 130	130		2,30	2,20	200	190
Fluting 135	135		2,35	2,25	210	200
Fluting 140	140		2,50	2,40	220	210
Fluting 150	150		2,60	2,50	230	220
Fluting 160	160		2,70	2,60	235	225

Test conditions 23°C | 50% RH | ISO 187

### Weener sales department

Micha Meyer | sales manager  
 micha.meyer@klingele.com  
 +49 163 77 22 345  
 +49 4951 303 24

### Technical customer service

Michael Michels | technical customer service  
 michael.michels@klingele.com  
 +49 173 95 80 442  
 +49 4951 303 45



**KLINGELE**  
 P A P I E R W E R K E

Klingele Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klingele-Str. 1 · 26826 Weener  
 Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klingele.com · www.klingele.com