

Testliner 3

effective from 01/2018

Brown testliner 3 | CEPI Code 30

Technical Specifications

| GRADE DESCRIPTION | Nominal grammage | Moisture content | SCT cd | | Bursting strength | |
|--------------------------|---------------------|------------------|-----------|---------|-------------------|------|
| | [g/m ²] | [%] | [kN/m] | | [kPa] | |
| Test Method | ISO 536 | ISO 287 | DIN 54518 | | ISO 2759 | |
| Tolerance | +/- 3% | | typ. | min. | typ. | min. |
| Testliner 115 | 115 | 7 – 9 | 2,10 | 2,00 | 290 | 280 |
| Testliner 120 | 120 | | 2,20 | 2,10 | 300 | 290 |
| Testliner 125 | 125 | | 2,25 | 2,15 | 310 | 300 |
| Testliner 130 | 130 | | 2,30 | 2,20 | 320 | 310 |
| Testliner 135 | 135 | | 2,35 | 2,25 | 330 | 320 |
| Testliner 140 | 140 | | 2,50 | 2,40 | 335 | 325 |
| Testliner 150 | 150 | | 2,60 | 2,50 | 350 | 340 |
| Testliner 160 | 160 | | 2,70 | 2,60 | 370 | 360 |
| Testliner 170 | 170 | | 2,80 | 2,70 | 380 | 370 |
| OPTIONAL | | | | | | |
| Cobb 60 sec DIN 535 | Testliner 115-170 | | | max. 60 | | |
| Cobb 1800 sec DIN 535 | Testliner 115-170 | | | max. 90 | | |

Test conditions 23°C | 50% RH | ISO 187

Weener sales department

Micha Meyer | sales manager
micha.meyer@klinge.de
+49 163 77 22 345
+49 4951 303 24

Technical customer service

Michael Michels | technical customer service
michael.michels@klinge.de
+49 173 95 80 442
+49 4951 303 45



KLINGELE
P A P I E R W E R K E

Klinge Papierwerke GmbH & Co. KG · Papierfabrik Weener · Dr.-Werner-Klinge-Str. 1 · 26826 Weener
Tel.: +49 4951 303 0 · Fax: +49 4951 303 52 · weener@klinge.de · www.klinge.de